


# **Opti Outlet Wall Panel**



#### **Product Information**

Wall Sandwich Panel

#### Üretim Yeri

İstanbul, İskenderun

#### **Uygulama Alanları**

- Industrial Buildings
- Military Buildings
- Public Buildings
- Agricultural Buildings
- Sports Facilities
- Construction Site Buildings
- Silos
- Hypermarkets
- Shopping Centers
- Storehouse Halls
- Administrative Buildings

and all other concrete structures with steel or prefabricated load bearing systems.

Assan Panel reserves the right to change the features of its products. The property rights of third parties must be respected. Acceptance of all orders is based on our current terms of sale and shipping. Users should always consider the latest edition of the Local Product Information Sheet for the relevant product, which can be obtained by contacting Assan Panel.





#### **Performance Advantages**

It has the good thermal insulation values.

Fast and trouble-free installation saves both time and labor.

Polyurethane does not retain water and does not harbor bacteria and insects.

Thanks to n-Pentane which is used to inflate the Polyurethane, no damage is caused to nature.

Thanks to its colored surface, additional coatings such as plaster and paint are not required.

It can be applied both horizontally and vertically.

It provides a visual advantage on facades thanks to the hidden connection element.

#### Measurements



Favorable Width	1000 mm
Minimum Height	3 meter
Maximum Height	13,5 meter

# Polyurethane (PUR)



Polyurethane Density (EN 1602)	33 ±6 kg/m <sup>3</sup>	
Polyurethane Density	40 mm	
Thermal Conductivity (EN 13165)	0,022-0,024 W/mK	
External Facing Thickness	0,45-0,30 mm	
Internal Facing Thickness	0,40-0,20 mm	
Steel Quality (EN 10327)  Dx51 D+Z Prepainted Galvanized Steel (last copaint on primer)		



# **Thermal Conductivity Values**

Thickness	Thermal Conductivity	Thermal Resistance	Thermal Resistance
	(W/m²K)	(m²K /W)	(ft² ºF h/Btu)
40 mm	0,575	1,739	9,875

# **Mechanical Properties**

Steel Surface Yield Strength	ce Yield Strength Min. 0,018 Mpa	
Panel Tensile Strength	Min. 0,095 Mpa	
Compressive Strength of Core Material	Min. 0,018 Mpa	


# **Tolerance Properties**

Panel Length	Panel Thickness	Panel Cover Width
If L<=3000 mm, -±5 mm; If L>3000 mm, ±10 mm	D ≤ 100mm ±2mm	±2 mm for all profiles

# **Standard Colour Option**



#### **Joint Details**




# **Transportation and Protection of Sandwich Panel**






Do not drag panels in a pile, or on the roof purlins. Lift panels from both ends when moving or laying in place.



Panels to be strored on site for long periods should be stacked in covered areas. Wherever possible, always place stacks preferably on wooden wedges, against ground water.



For shorter periods, stacks should be arranged on sloppy areas with a simple scaffolding and polyethilen cover, leaving space for ventilation. Place stacks on a simple wedge.



Do not walk on panels.